

33 Stapleton Street

Winnipeg, Manitoba, Canada, R2L 1Z9

Toll Free U.S.A. & Canada **1-800-409-3484**

Ph. 204 988-3484

Fax 204 988-3480

ADHESION PROMOTER

DATA SHEET

Pro Tech Adhesion Promoter is a non conductive water based adhesion promoter (substrate modifier) that promotes the adhesion to T.P.O., T.P.E., T.E.O., Polypropylene and Polyethylene plastics.

After drying, our Adhesion Promoter allows for the adhesion of; automotive basecoats, primers, polyurethane foams, inks and adhesives to the above substrates.

Pro Tech Adhesion Promoter should be applied as received using conventional spray equipment. A wet film thickness of between 2 – 4 mils is needed to obtain a dry film thickness of between .2 - .4 mils dry. Pro Tech Adhesion Promoter may also be wiped on (avoid to thick of a build up as drying time will be longer). Accelerated drying may be achieved with the use of an Infrared heat system or a heat gun.

Drying time @ 77F = 3 to 4 minutes

Infrared Heat System = 30 to 40 seconds

Heat Gun = 30 to 40 seconds